

# CRYLCOAT® 2606-3    CRYLCOAT 2664-3 CRYLCOAT 2666-3

Powder Coating Resins



CRYLCOAT 2606-3, CRYLCOAT 2664-3, CRYLCOAT 2666-3 - have been especially designed to respond best to the requirements of a variety of outdoor architectural applications with superior water-spot resistance to comply with GSB and Qualicoat certifications.



## Value Proposition


- Water-spot improved resins
- Excellent outdoor weatherability
- Good mechanical and overall performance
- Tribo enhanced

### Water-spot test [58°C] (\*)


Segment	A	A	A+	A+	A+	A+
CRYLCOAT®	2664-3	2618-3	2606-3	2616-3	2666-3	2686-3
Viscosity [mPas]	3200	3100	4,800	4,250	3,500	3,300
Hardener	95/5 XL552	95/5 XL552	95/5 XL552	95/5 XL552	95/5 XL552	95/5 XL552
Ratio Binder/pigment [%]	70	70	70	70	70	70
Curing [°C x min]	180 x 10	180 x 10	180 x 10	180 x 10	180 x 10	180 x 10
Tg [°C]	58	61	66	67	58	55
ΔL	2.1	4.2	1.0	3.8	1.7	4.2

(\*) Test method according to GSB AL 631, International Quality Regulations For the Coating of Aluminum Building Components, Edition January 2012, Chapter 9.17 - Resistance to Moisture.


#### Florida test CRYLCOAT 2606-3



#### Florida test CRYLCOAT 2664-3



#### Florida test CRYLCOAT 2666-3



### CRYLCOAT 2606-3, CRYLCOAT 2664-3, CRYLCOAT 2666-3

Available now for customers in the Europe, Middle East, Africa (EMEA) and Asia Pacific regions, our CRYLCOAT 2606-3, CRYLCOAT 2664-3, CRYLCOAT 2666-3 outperform architectural Primid® grades in moisture resistance test.

Disclaimer: allnex Group companies ('allnex') decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any allnex and/or third party intellectual property rights. The user should perform his/her own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of allnex and/or third parties remains the sole responsibility of the user.

Notice: Trademarks indicated with ®, ™ or \* as well as the allnex name and logo are registered, unregistered or pending trademarks of Allnex Netherlands B.V. or its directly or indirectly affiliated allnex Group companies.

©2018 allnex Group. All Rights Reserved.

**Email: [custinfo@allnex.com](mailto:custinfo@allnex.com) - Worldwide Contact Info: [www.allnex.com](http://www.allnex.com)**